

### TM-HT-170 Heat Transfer Fluid

TM-HT-170 is part of Tyrell Chemical's perfluoropolyether (PFPE) line of inert, dielectric heat transfer fluid. Designed for extreme conditions, these high-performance fluids are part of a product line that features a wide range of boiling points. TM-HT-170 fluids have a high boiling point of 170°C and are generally compatible with plastics, elastomers and metals. TM-HT-170 fluids have no fire, flash or auto-ignition points and are inflammable.

## **Applications**

- Semiconductor manufacturing
- Pharmaceutical manufacturing
- Chemical manufacturing
- Vapor phase heating
- Transformers
- Recirculating chillers
- Compute cooling

## **Properties and Usage Benefits**

- Optimal thermal transfer and performance
- Reduced evaporation losses
- Wide material compatibility with no corrosion, degradation or decomposition residues
- No toxicity, flammability, or explosion hazards

# **Material Compatibility**

#### Metals

 Copper, brass, iron, nickel, stainless steel, aluminum, bronze, AISI 316

#### **Plastics**

Polycarbonate, polypropylene, ABS copolymer, polyphenyloxide, PE low density, PET, POM, PTFE, PVC, PMMA

#### **Elastomers**

 Natural rubber, silicone rubber, butyl rubber, fluorosilicone, NBR, EPDM

\*Safe with hydrocarbon-based plasticizers that allow for compatibility with almost all seals and gaskets

Distributed by Fisher Scientific. Contact us today:

#### In the United States

Order online: fishersci.com
Call customer service: 1-800-766-7000

Properties	
Tyrell Part #	TM-HT-170
Fisher Scientific Part # (Air Freight)	502120255
Fisher Scientific Part # (Sea Freight)	502120256
Туре	PFPE
Boiling point	170 °C
Pour point	-97 ℃
Density	1.77 g/cm3
Kinematic viscosity	1.8 cSt
Vapor pressure	0.8 torr
Specific heat	0.23 cal/g⋅°C
Heat of vaporization at boiling point	16 cal/g
Refractive index	1.28
Coefficient of thermal expansion	0.0011 .℃
Surface tension	18 dyne/cm
Thermal conductivity	0.065 W/m-K
Dielectric strength	40 kV
Dielectric constant	1.94
Volume resistance	1.5·10 <sup>15</sup> Ohm∙cm
Average molecular weight	760 amu
Dissipation factor (1 Khz)	2.10-4
Solubility of water	14 ppm (wt)
Solubility of air	26 cm <sup>3</sup> gas

## Safety

HT fluids are safe to handle as they are inert, noncorrosive, nonflammable and nontoxic. HT fluids possess no flash, fire or auto-ignition points.

